

























TECHNICAL CHARACTERISTICS

wineo 600 wineo

Covering type according to EN ISO 10582: Heterogeneous resilient-flooring to glue

	wineo 600 wood	wineo 600 wood XL	wineo 600 stone	wineo 600 stone XL	
					
Format	1200 x 180 mm	1505 x 235 mm	609,6 x 304.8 mm	900 x 450 mm	
Product thickness	2 mm	2 mm	2 mm	2 mm	
Planks, tiles / m² per box	18 / 3.89 m ²	12 / 4.24 m ²	18 / 3.34 m ²	12 / 4.86 m ²	
Boxes / m² per pallet	60 / 233.40 m ²	64 / 271.36 m ²	72 / 240.48 m ²	50 / 243.00 m ²	
Guarantee	20 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de				
Classification					Product composition
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874		Corridors, living rooms, kitchens, home offices		1 Surface sealing
	Utilization class 32 Normal use in the commercial sector EN ISO 10874		Offices, boutiques, cafés		2 Wear layer Thickness 0.4 mm
	Utilization class 41 Medium use in the light industrial sector EN ISO 10874		Workshop for precision mechanics		3 Decor film Surface texture - various embossings
	Wear resistance EN 660-2		Group T		4 Base layer
	Reaction to fire EN 13501-1		B _{fl} - s1		5 Backing
	R9 Anti slip category DIN 51130		R 9		DESIGN FLOORING to glue 
	Slip resistance EN 13893		$\mu \geq 0.30$ - DS		
	Anti-static properties EN 1815		≤ 2 kV		Certifications
	Staining and chemical resistance EN ISO 26987		Good resistance according to the concentration and residence time		 windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf - 07 - Elastischer Bodenbelag DOP: 0401001 EN 14041:2004  Resilient Flooring to be used within a building.  <small>Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</small>  Schadstoffgeprüft Emissionsgeprüft  TO 710 4061-1  factory made coated
	Light fastness EN ISO 105-B02		≥ 6		
	Residual indentation EN ISO 24343-1		~ 0.02 mm		
	Castor chair test EN 425 / ISO 4918		Type W – no visible change		
	Thermal resistance EN 12667		~ 0.01 (m ² K)/W		
	Impact sound reduction EN ISO 16251-1		~ 4 dB		
	Dimension stability EN ISO 23999		~ 0.15 %		
	Disposal		Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203		

Relevant information:

- Installation in utilization class 41 possible (vehicular traffic excluded).
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.